

Component - Plastics

E245249

Envalior

Flughafenstrasse 101, Dusseldorf 40474 DE

AKV30H2.0+, ECOAKV30H2.0+, AKV30H2.0+LT, AKV30H3.0+, AKV30H3.0LT+

Polyamide 66 (PA66), glass reinforced "DURETHAN", furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI	HAI	RTI Elec (°C)	RTI Imp (°C)	RTI Str (°C)
ALL	0.75	HB	4	0	125	90	110
	1.5	HB	4	0	125	105	115
	3.0	HB	3	0	125	105	115
	6.0	HB	1	0	125	105	115
Comparative Tracking Index (CTI):			1	Inclined Plane Tracking (IPT) kV:			-
Dielectric Strength (kV/mm):			25	Volume Resistivity (10 ^x ohm-cm):			11
High-Voltage Arc Tracking Rate (HVTR):			1	Surface Resistivity (10 ^x ohms/square):			-
Dimensional Change (%):			0.0	High Volt, Low Current Arc Resis (D495):			6

+ - Material designations may be followed by suffix numbers and/or letter(s) denoting color.

ANSI/ UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1979-04-13

Last Revised: 2023-03-15

© 2024 UL Solutions



© 02/2024 by NORWE GmbH

All dimensions in mm/inch

The permissible deviations according to DIN 16901 apply as tolerances

Warranties:
refer to Terms and Conditions of Sale



Valid version of
data sheet online

QR Online-Version

NORWE GmbH

Paulstraße 5, Pernze
51702 Bergneustadt
Deutschland

Telefon +49 (0) 27 63-807-0
E-mail verkauf@norwe.de
Internet www.norwe.de
www.norwe.eu

NORWE Inc.

P.O. Box 25 11
North Canton, OH 44720-0511
United States of America

Telefon +1-330 497-8113
E-mail usa@norwe.com
Internet www.norwe.com

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	0.75	HB, HB75 (ALL)
			1.5	HB, HB75 (ALL)
			3.0	HB, HB40 (ALL)
			6.0	HB, HB40 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	°C	0.75	700
			1.5	700
			3.0	700
			6.0	700
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	°C	0.75	725
			1.5	725
			3.0	750
			6.0	750
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC AC Dielectric Strength (AC DS)	IEC 60243-1	kV/mm	-	-
IEC DC Dielectric Strength (DC DS)	IEC 60243-2	kV/mm	-	-
IEC Volume Resistivity (VR)	IEC 62631-3-1	10 ^x ohm-m	-	-
IEC Surface Resistivity (SR)	IEC 62631-3-2	10 ^x ohms	-	-
IEC Inclined Plane Tracking (IPT)	IEC 60587	kV	-	-
IEC Ball Pressure	IEC 60695-10-2	°C	-	258
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-1	kJ/m ²	-	-

© 02/2024 by NORWE GmbH

All dimensions in mm/inch

The permissible deviations according to DIN 16901 apply as tolerances

Warranties:
refer to Terms and Conditions of Sale



Valid version of
data sheet online

QR Online-Version

NORWE GmbH

Paulstraße 5, Pernze
51702 Bergneustadt
Deutschland

Telefon +49 (0) 27 63-807-0
E-mail verkauf@norwe.de
Internet www.norwe.de
www.norwe.eu

NORWE Inc.

P.O. Box 25 11
North Canton, OH 44720-0511
United States of America

Telefon +1-330 497-8113
E-mail usa@norwe.com
Internet www.norwe.com