

Component - Plastics

E41938

## CELANESE INTERNATIONAL CORP - Florence

8040 DIXIE HWY, FLORENCE, KY 41042-2904 United States

### FR530(I)(+)(f1), FR530L(I)(+)(f1)

Polyethylene Terephthalate (PET) "Rynite", glass reinforced, flame retardant, furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI (PLC)	HAI (PLC)	GWIT (°C)	GWFI (°C)	RTI Elec (°C)	RTI Imp (°C)	RTI Str (°C)
NC, BK	0.35	V-0	3	1	--	--	155	155	155
ALL	0.75	V-0	2	1	800	960	155	155	155
NC, BK	1.5	V-0, 5VA	0	1	800	960	155	155	155
ALL	2.0	V-0, 5VA	0	1	985	960	155	155	155
	3.0	V-0, 5VA	0	1	985	960	155	155	155

Comparative Tracking Index (CTI) (PLC):	2	IEC Comparative Tracking Index (V):	--	IEC CTI Material Group:	--
Inclined Plane Tracking (IPT) (kV):	--	High-Voltage Arc Tracking Rate (HVTR) (PLC):	1	Dielectric Strength (DS) (kV/mm):	34
Volume Resistivity (VR) (10 <sup>x</sup> ohm cm):	16	Surface Resistivity (SR) (10 <sup>x</sup> ohms/square):	--	High Volt, Low Current Arc Resis (D495):	6

(+) - Use of Re grind up to 50% by weight inclusive, has the same basic material characteristics. (f1) - Suitable for outdoor use with respect to exposure to Ultraviolet Light, Water Exposure and Immersion in accordance with UL 746C. (I) - Recognized ground insulation component at 0.4 mm with MW79 in UL1446 Class 155 electrical insulation system designated R201N (File E69939). (1) Material designations that are color pigmented may be followed by suffix letters and numbers. (2) may be prefixed by ZYT for Zytel or MIN for Minlon or CRA for Crastin or RYN for Rynite.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1996-01-04

Last Revised: 2025-11-14

© 2026 UL Solutions



#### © 04/2026 by NORWE GmbH

All dimensions in mm/inch

The permissible deviations according to DIN 16901 apply as tolerances

Warranties:  
refer to Terms and Conditions of Sale



Valid version of data sheet online

QR Online-Version

#### NORWE GmbH

Paulstraße 5, Pernze  
51702 Bergneustadt

Deutschland

Telefon +49 (0) 27 63-807-0  
E-mail verkauf@norwe.de  
Internet www.norwe.de  
www.norwe.eu

#### NORWE Inc.

P.O. Box 25 11  
North Canton, OH 44720-0511  
United States of America

Telefon +1-330 497-8113  
E-mail usa@norwe.com  
Internet www.norwe.com

ISO/IEC Flammability Properties	Value	Test Method
<b>Flammability</b>		IEC 60695-11-10
0.35 mm, Color: NC, BK	V-0	
0.75 mm, Color: ALL	V-0	
1.5 mm, Color: NC, BK	V-0	
2.0 mm, Color: ALL	V-0	
3.0 mm, Color: ALL	V-0	
<b>Flammability</b>		IEC 60695-11-20
1.5 mm, Color: NC, BK	5VA	
2.0 mm, Color: ALL	5VA	
3.0 mm, Color: ALL	5VA	
<b>Glow Wire Ignition Temperature (GWIT)</b>		IEC 60695-2-13
0.75 mm	800 °C	
1.5 mm	800 °C	
2.0 mm	985 °C	
3.0 mm	985 °C	
<b>Glow Wire Flammability Index (GWFI)</b>		IEC 60695-2-12
0.75 mm	960 °C	
1.5 mm	960 °C	
2.0 mm	960 °C	
3.0 mm	960 °C	

**© 04/2026 by NORWE GmbH**

All dimensions in mm/inch

The permissible deviations according to DIN 16901 apply as tolerances

Warranties:  
refer to Terms and Conditions of Sale



Valid version of data sheet online

QR Online-Version

**NORWE GmbH**

Paulstraße 5, Pernze  
51702 Bergneustadt  
Deutschland

Telefon +49 (0) 27 63-807-0  
E-mail verkauf@norwe.de  
Internet www.norwe.de  
www.norwe.eu

**NORWE Inc.**

P.O. Box 25 11  
North Canton, OH 44720-0511  
United States of America

Telefon +1-330 497-8113  
E-mail usa@norwe.com  
Internet www.norwe.com